



国际电工委员会 (IEC) 404-8-1标准 The IEC (IEC404-8-1) Standard of Ferrite Magnet

| 性能 | 剩磁感应强度 | 矫顽力 | 内禀矫顽力 | 最大磁能积 | | 密度 |
|-----------------------------------|-----------|----------------|--------------------------|-------------|-------|---------|
| Properties | Remanence | Coercive Force | Intrinsic Coercive Force | Max. Energy | Urec | Density |
| 牌号 | Br | HcB | HcJ | (BH) max | | |
| Grade | MT | kA/m | kA/m | KJ/m3 | Gs/Oc | G/cm3 |
| 各向同性isotropy hard tarrite 7/21 | 190 | 125 | 210 | 6.5 | 1.2 | 4.9 |
| 各向异性anisotropy hard tarrite 20/19 | 320 | 170 | 190 | 20 | 1.1 | 4.8 |
| 各向异性anisotropy hard tarrite 20/28 | 320 | 170 | 190 | 20 | 1.1 | 4.8 |
| 各向异性anisotropy hard tarrite 24/23 | 350 | 215 | 230 | 24 | 1.1 | 4.8 |
| 各向异性anisotropy hard tarrite 25/14 | 380 | 130 | 135 | 25 | 1.1 | 5 |
| 各向异性anisotropy hard tarrite 25/22 | 370 | 205 | 220 | 25 | 1.1 | 4.8 |
| 各向异性anisotropy hard tarrite 26/18 | 370 | 175 | 180 | 26 | 1.1 | 5 |

Contact Information

China Magnets Source Material Ltd.

Tower B, Qiongzhu Building, Huawang Rd,

LongHua District, Shenzhen, China 518109

Telephone: +86 755 28174720

Fax: +86 755 28174720

Email: sales@china-magnets-source-material.com

Website: www.china-magnets-source-material.com

www.cms-permanentmagnet.com