

**国际MMPA(0100-87)标准 The International MMPA (0100-87) Standard of Ferrite Magnet**

性能 Properties	剩磁感应强度 Remanence		矫顽力 Coercive Force		内禀矫顽力 Intrinsic Coercive Force		最大磁能积 Max. Energy	
牌号 Grade	Br		HcB		HcJ		(BH) max	
	MT	kGs	kA/m	KOe	kA/m	KOe	KJ/m3	MGOe
C1	230	2.3	1.48	1.86	2.58	3.5	8.36	1.05
C5	380	3.8	191	2.4	199	2.5	27	3.4
C7	340	3.4	258	3.23	318	4	21.9	2.75
C8A	385	3.85	235	2.95	242	3.05	27.8	3.5
C8b	420	4.2	232	2.913	236	2.96	32.8	4.12
C9	380	3.8	280	3.516	320	4.01	26.4	3.32
C10	400	4	288	3.617	280	3.51	30.4	3.82
C11	430	4.3	200	2.512	204	2.56	34.4	4.32

**Contact Information**

China Magnets Source Material Ltd.

Tower B, Qiongzhu Building, Huawang Rd,  
LongHua District, Shenzhen, China 518109

Telephone: +86 755 28174720

Fax: +86 755 28174720

Email: [sales@china-magnets-source-material.com](mailto:sales@china-magnets-source-material.com)

Website: [www.china-magnets-source-material.com](http://www.china-magnets-source-material.com)

[www.cms-permanentmagnet.com](http://www.cms-permanentmagnet.com)