



国际电工委员会（IEC）404-8-1标准 The IEC (IEC404-8-1) Standard of Ferrite Magnet

性能	剩磁感应强度	矫顽力	内禀矫顽力	最大磁能积		密度
Properties	Remanence	Coercive Force	Intrinsic Coercive Force	Max. Energy	Urec	Density
牌号	Br	HcB	HcJ	(BH) max		
Grade	MT	kA/m	kA/m	KJ/m3	Gs/Oc	G/cm3
各向同性isotropy hard Ferrite 7/21	190	125	210	6.5	1.2	4.9
各向异性anisotropy hard Ferrite 20/19	320	170	190	20	1.1	4.8
各向异性anisotropy hard Ferrite 20/28	320	170	190	20	1.1	4.8
各向异性anisotropy hard Ferrite 24/23	350	215	230	24	1.1	4.8
各向异性anisotropy hard Ferrite 25/14	380	130	135	25	1.1	5
各向异性anisotropy hard Ferrite 25/22	370	205	220	25	1.1	4.8
各向异性anisotropy hard Ferrite 26/18	370	175	180	26	1.1	5

Contact Information

China Magnets Source Material Ltd.

Tower B, Qiongzhu Building, Huawang Rd,
LongHua District, Shenzhen, China 518109

Telephone: +86 755 28174720

Fax: +86 755 28174720

Email: sales@china-magnets-source-material.com

Website: www.china-magnets-source-material.com
www.cms-permanentmagnet.com